### PCT

# WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



# INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

SE

(51) International Patent Classification 6: (11) International Publication Number: B32B 27/10, 27/08, B65D 65/40 A1

WO 97/02140

(43) International Publication Date: 23 January 1997 (23.01.97)

(21) International Application Number: PCT/SE96/00829

(22) International Filing Date: 25 June 1996 (25.06.96)

3 July 1995 (03.07.95)

(71) Applicant (for all designated States except US): TETRA

LAVAL HOLDING & FINANCE S.A. [CH/CH]; Avenue Général-Guisan 70, CH-1009 Pully (CH).

(72) Inventor; and (75) Inventor/Applicant (for US only): MAGNUSSON, Katarina [SE/SE]; Assarhusavägen 214, S-240 17 Södra Sandby (SE).

(74) Agents: STRÖM, Tore et al.; Ström & Gulliksson AB, P.O. Box 4188, S-203 13 Malmö (SE).

(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).

#### **Published**

With international search report. In English translation (filed in Swedish).


(54) Title: PACKAGING LAMINATES BASED ON CARDBOARD AND PAPER

#### (57) Abstract

(30) Priority Data:

9502393-3

A folded moisture and heat resistant container is manufactured of a material of laminate type in the form of a sheet or a web, said laminate comprising at least a base layer (1), an outer coating (2) and an inner coating (3). The material is at least on one side thereof heat treated in humid atmosphere at a temperature of 85 °C or more. In the material the base layer (1) consists of a liquid absorbing material, the outer coating (2) consists of a polymer selected from the group including polypropylene, oriented polypropylene, metalized oriented polypropylene, high density polyethylene, metalized high density polyethylene, linear low density polyethylene, polyester, metalized



polyester and amorphous polyester, and the inner coating (3) consists of a polymer selected from the goup including polypropylene, high density polyethylene, linear low density polyethylene, polyester and amorphous polyester.

### FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
ΑŪ	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	ΙT	Italy	PL	Poland
BJ	Benin	JP	Јарап	PT	-Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgystan	RU	Russian Federation
	Canada	KP	Democratic People's Republic	SD	Sudan
CA	Central African Republic	•••	of Korea	SE	Sweden
CF		KR	Republic of Korea	SG	Singapore
CG	Congo Switzerland	KZ	Kazakhstan	SI	Slovenia
CH		LI	Liechtenstein	SK	Slovakia
CI	Côte d'Ivoire	LK	Sri Lanka	SN	Senegal
CM	Cameroon	LR	Liberia	SZ	Swaziland
CN	China	LT	Lithuania	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
CZ	Czech Republic	LV	Latvia	TJ	Tajikistan
DE	Germany	MC	Monaco	TT	Trinidad and Tobago
DK	Denmark	-	Republic of Moldova	UA.	Ukraine
EE	Estonia	MD MG	•	UG	Uganda
ES	Spain		Madagascar	US	United States of America
FI	Finland	ML	Mali	UZ	Uzbekistan
FR	France	MN	Mongolia	VN	Viet Nam
GA	Gabon	MR	Mauritania	VIC	A MCC 134411

### PACKAGING LAMINATES BASED ON CARDBOARD AND PAPER

The present invention relates to a container which is manufactured from a material of laminate type in the form of a sheet or a web. More specifically the invention relates to a folded moisture and heat resistant container which is manufactured from a material of laminate type in the form of a sheet or a web, which material comprises a base layer, an outer coating and an inner coating, the material on at least one side thereof being heat treated in a humid atmosphere at a temperature of 85 °C or higher.

The demand on a container intended for foods is that it should be easy to manufacture and handle as well as be designed and constructed in such a way that it gives the best protection possible to the products which are to be filled and transported in the container. A good product protection implies among other things that the container should be sufficiently mechanically strong and dimensional stable in order to withstand the outer influences which the container is exposed to during normal handling without the container being deformed or destroyed. Furthermore, the container should be sufficiently physically and chemically impermeable in order to prevent transport of liquid and/or gases through the walls of the container.

15

20

25

30

35

Paper and board are cheap package materials. However, they also have drawbacks in rapidly loosing their mechanical strength properties when exposed to liquid or moisture, which results in that a container containing these materials becomes flabby and cumbersome. It has thus been necessary to improve the properties of the material, either by coating or lamination.

Known packaging laminates of this kind comprise a base layer of paper or board, which gives the container strength and dimensional stability, as well as an outer layer of plastic, preferably polyethylene, which gives the container necessary impermeability properties against

2

liquid and furthermore makes the packaging laminate heat sealable in such a way that two plastic layers facing each other easily can be sealed by the surfaces being melted together during the manufacturing of the container, whereby mechanically stable liquid impermeable sealing joints are formed.

In order to be able to use the packaging laminate in containers for products of different compositions the laminate must be supplemented with at least one additional layer of a material with barrier properties, and the hitherto most used barrier material is a metal foil, preferably an aluminium foil (Al foil). Furthermore, an Al foil applied on the inside of the laminate must be covered by one or several plastic layers, usually polyethylene, in order to prevent contact between the Al-foil and the later on filled food.

10

15

20

25

It has thus always been a wish within the packaging technology to find alternative package materials in which liquid absorbing fibber layers are not used, these materials in practice thus being completely free from the disadvantages of the known package materials based on paper or cardboard.

Such a known alternative package material has for example a strengthening base layer of plastic and a filler intermixed with the plastic, and this material has proved to be less moisture sensitive than the previously used materials based on paper and cardboard.

Furthermore, it is often required that a container intended for food is constructed in such a way that it allows aseptic filling of a product which is sterilized and filled under sterile conditions in a likewise sterilized container which after filling is sealed in such a way that while stored before being consumed the filled product is not reinfected by harmful micro-organisms.

3

Concerning the filled product, it has for a long time been known that the shelf life of a foodstuff can be prolonged by the foodstuff being subjected to a heat treatment which is so extensive that micro-organisms present in the foodstuff are completely killed or reduced in number. In order to achieve an adequate heat treatment the treatment must be performed in such a way that all parts of the treated product once and for all is heated to such an extent and for such a long time as is required for obtaining the desired killing or inactivation of micro-organisms in the product.

10

20

25

30

A heat treatment for killing and/or inactivation of micro-organisms can be accomplished by means of moist as well as dry heat. In the food industry a heat treatment in moist heat is preferred since the biological killing and inactivating mechanisms are much more effective at a high water content than at a low water content, i.e. dry heat. Besides, the heat transfer in the equipment used for heat treatment is much more effective with moist heat.

However, known containers of a packaging laminate with a liquid absorbing fibber layer cannot be used for heat treatment with moist heat without the desired mechanical rigidity of the packaging laminate and thus the dimensional stability of the container being impaired or lost.

The purpose of the invention is thus to provide a moisture and/or heat resistant packaging container made of a laminate material of the above mentioned type.

In order to achieve this purpose the packaging material according to the invention has obtained the characterizing features of claim 1.

In order to explain the invention in more detail reference is made to the accompanying drawing in which

Fig. 1 schematically shows a cross section through a packaging laminate in the form of a sheet or a web according to the invention.

Like conventional packaging laminates, the packaging laminate in Fig. 1 comprises a relatively thick strengthening base layer 1 as well as an outer coating 2 and an inner coating 3. An outer and an inner coating refers to a coating which is applied on the outside or the inside of the laminate, respectively.

10

15

20

25

30

35

The packaging laminate has as an essential part a base layer 1 of a liquid absorbing material. Other layers in the packaging laminate can also include liquid absorbing materials. However, these are not so important for the container stability as the base layer with its mechanical strength properties.

The liquid absorbing material in the base layer 1 preferably consists of paper or cardboard. Other water absorbing materials used in packaging laminates are for example ethylene/vinyl alcohol, i.e. an ethyl-vinyl alcohol copolymer (EVOH) and polyvinyl alcohol. These polymers rapidly loose their barrier properties if they are exposed to moisture.

It has surprisingly been shown that containers made of a laminate of the above mentioned type not only withstand the usual heat treatment but also a treatment under extreme conditions in a humid environment if the laminate with the above mentioned liquid absorbing base layer 1 also comprises the outer coating 2 as well as the inner coating 3 with the alternative components indicated below in the laminate layers.

Furthermore, the cut edges on the packaging laminate in the completed container should be protected according to a simultaneously filed patent application.

In order to withstand a strong influence of moisture in the form of water as liquid or steam the coatings 2 and

10

15

20

25

30

35

are according to the invention designed to be heat resistant and to have good vapour barriers. Thus, the outer coating 2 consists of a polymer which can be polypropylene, oriented polypropylene, metalized (usually with aluminium) oriented polypropylene, high density polyethylene, linear low density polyethylene, metalized high density polyethylene, polyester, metalized (usually with aluminium) oriented polyester or amorphous polyester, the polyester for example being polyethylene terephtalate. The inner coating 3 consists of a polymer which can be polypropylene, high density polyethylene, linear low density polyethylene, polyester or amorphous polyester, the polyester for example being polyethylene terephtalate.

Preferably, the packaging laminate according to the invention also has a barrier layer 4 arranged between the base layer 1 and the inner coating 3, which barrier layer 4 is intended to be facing the filling material of the packaging container. The barrier layer can consist of aluminium, a silica coating, ethylene/vinyl alcohol, polyvinyl alcohol, metalized (usually with aluminium) oriented polypropylene, an aluminium oxide coating or metalized (usually with aluminium) oriented polyester, the polyester for example being polyethylene terephtalate.

Furthermore, the packaging laminate according to the invention can have a layer 5 arranged between the base layer and the outer coating 2, which layer 5 can consist of polypropylene, low density polyethylene, medium density polyethylene, high density polyethylene or amorphous polyester, the polyester for example being polyethylene terephtalate. An additional similar layer can be arranged on the other side of the base layer 1.

Finally, the packaging laminate according to the invention can have a coating 6 adjacent one or both sides of the barrier layer 4, which coating 6 can consist of an adhesive plastic, a heat sealable plastic (e.g.

6

polyethylene), a primer or a lacquer. An additional layer can be incorporated between the base layer 1 and the adjacent coating 6, which layer then preferably consists of one of the above mentioned components for the layer 5.

5

10

20

25

30

35

Consumer containers ready for use and of throw-away type are according to known technology manufactured by folding from a web of a packaging laminate according to the invention to a tube in such a way that the two longitudinal edges of the web are joined in a longitudinal overlap seam. The tube is filled at 80-90 °C with the filling material in question and is divided into closed container units by repeated lateral sealing of the tube beneath the level of filling material in the tube. Container units filled by means of this web filling method are separated from each other by cuts in the transversal sealing zones and the desired geometrical final form is obtained by an additional forming and sealing operation.

The packaging laminate according to the invention is not only adapted to the above mentioned treatment but also to more drastic conditions including moisture and/or heat. Thus, containers manufactured from these laminates are very suitable for preservation by refrigeration as well as preservation by heat. When preservation by refrigeration is used these containers having solid and/or liquid filling material can be chilled by means of water cooling.

Furthermore, the laminate according to the invention has been shown to be very suitable for manufacturing dimensional stable impermeable packaging containers which can be used at highly extreme conditions in a humid environment including heat treatment with moist heat and a pressure above the atmospheric, at least one of the sides of the container being exposed to a humid atmosphere and heat treatment. Such harsh environments comprise autoclaving at temperatures and periods which are customary for foods. This means that the laminate is also extremely

suitable to be used for producing a container which is intended for being filled with a product under aseptic conditions. In this connection the product is sterilized and filled under almost sterile conditions in a likewise sterilized container which after filling is sealed in such a way that during storage the filled product is not reinfected by micro-organism before it is consumed.

When such a packaging procedure, a so called hotfill, is used the filling material is thus filled according to known technology while still being hot in sterilized, preferably heat sterilized containers. Such a treatment results in that the container is exposed to moist heat at a temperature of the filling material of 75 °C, preferably 90 °C, or more.

10

15

20

25

30

35

During a subsequent cooling phase containers exposed to the above mentioned example of heat treatment will also be subjected to environments in which good sealing properties of the container against moisture and liquid are required. During the cooling phase the filling material is allowed to cool in the container which is manufactured from a laminate. This cooling can for example take place in a fluid bath and also by spraying with cold water, if necessary with accompanying cooling with CO<sub>2</sub> or N<sub>2</sub> in order to rapidly be able to achieve a sufficiently low temperature, such as 4 °C.

The above mentioned harsh environments comprise autoclaving at temperatures and periods customary for food. In this connection autoclaving means sterilising or killing micro-organisms in a vessel, in which the heating takes place under pressure, usually with steam or air as a heat transfer medium.

At a temperature in the autoclaving vessel within the interval 105-121 °C an established reference temperature is chosen to be 121.1 °C (250 °F) and a z-value (a temperature alteration for changing the reduction time for a certain

8

micro-organism with a factor 10) to be 10 °C. The heat treatment value  $F_r$  which is determined in this area is often represented by  $F_0$ . ( $F_0 = F_r$  at 121 °C). The heat treatment value  $F_r$  is thus the combined lethal effects at the temperatures used in practice. When the temperature lies within the interval 90-105 °C during production a reference temperature of 93.3 °C (200 °F) and a z value of 10 °C are used. For pasteurization a reference temperature of 65.5 °C (150 °F) and a z value of 5 °C are used. Other standardized reference temperatures are used at special occasions.

10

20

Products included in a container according to the invention are not heat treated to a special  $F_r$  value, on the contrary to a certain centre temperature guaranteeing a product which is sufficiently heat treated. (The position of the centre point depends of course on the construction of the container as well as the product in the container.)

Containers according to the invention have been shown to be useful for liquid products requiring an  $F_0$  value of 3-5, for viscous/semi-solid products requiring an  $F_0$  value of 6-10 and also for hard products requiring an  $F_0$  value of 12-18, the  $F_0$  values of course being dependent of the volume of the container.

15

### CLAIMS

- A folded moisture and heat resistant container manufactured of a material of laminate type in the form of a sheet or a web, said laminate comprising at least one base layer (1), an outer coating (2) and an inner coating (3), the material on at least one side thereof being heat treated in a humid atmosphere at a temperature of 85 °C or more, characterized in that the base layer (1) consists of a liquid absorbing material, the outer coating (2) consists of a polymer selected from the group including polypropylene, oriented polypropylene, metalized oriented polypropylene, high density polyethylene, metalized high density polyethylene, linear low density polyethylene, polyester, metalized polyester and amorphous polyester, and the inner coating (3) consists of a polymer selected from the group including polypropylene, high density polyethylene, linear low density polyethylene, polyester and amorphous polyester.
- 2. A material as claimed in claim 1, characterized in that the base layer (1) consists of paper or cardboard.
- 3. A material as claimed in claim 1,
  c h a r a c t e r i z e d in that the material between the
  25 base layer (1) and the inner coating (3) additionally
  includes a barrier layer (4) selected from the group
  including aluminium, an aluminium oxide coating, a silica
  coating, ethylene/vinyl alcohol, polyvinyl alcohol,
  metalized oriented polyester and metalized oriented
  30 polypropylene.
  - 4. A material as claimed in claim 1, c h a r a c t e r i z e d in that the material additionally includes a layer (5) between the base layer (1) and the outer coating (2), said layer (5) being selected from the group including polypropylene, low

density polyethylene, medium density polyethylene, high density polyethylene and amorphous polyester.

5. A material as claimed in claim 3, c h a r a c t e r i z e d in that the material additionally includes a coating (6) adjacent one or both sides of the barrier layer (4), said coating (6) being selected from the group including an adhesion plastic, a heat sealable plastic, a primer and a lacquer.

1/1




FIG 1

# INTERNATIONAL SEARCH REPORT

International application No.
PCT/SE 96/00829

		PC1/SE 96/00	1023
A. CLASSI	FICATION OF SUBJECT MATTER		
	2B 27/10, B32B 27/08, B65D 65/40 International Patent Classification (IPC) or to both national	d classification and IPC	
	SEARCHED		
Minimum doo	cumentation searched (classification system followed by clas	sification symbols)	
IPC6: B3	2B, B65D, B65B		at a Salda asserbad
Documentatio	on searched other than minimum documentation to the exte	ent that such documents are included in	n the neids searched
SE,DK,FI	,NO classes as above		
Electronic da	ta base consulted during the international search (name of c	lata base and, where practicable, searc	h terms used)
RM25, EI	PODOC, PAJ, WPI		
C. DOCU	MENTS CONSIDERED TO BE RELEVANT	neighbor of the relevant nassages	Relevant to claim No.
Category*			
A	EP 0532766 A1 (JUJO PAPER CO., LTD 24 March 1993 (24.03.93), page line 10 - line 52; page 3, lin line 9, abstract	2.	1-5
A	EP 0502330 A2 (IDEMITSU PETROCHEMI 9 Sept 1992 (09.09.92), page 2 page 6, line 26 - line 29, abs	1-5	
A	US 4919984 A (MARAUHASHI ET AL), 2 (24.04.90), column 4, line 57 line 56 - column 9, line 14, 2	- line 62; column 8,	1,3-5
	Day of Pay	C. X See patent family an	inex.
Speri	ther documents are listed in the continuation of Box at categories of cited documents:	To later document published after the	international filing date or priorit
to be	ment defining the general state of the art which is not considered of particular relevance document but published on or after the international filing date ment which may throw doubts on priority claim(s) or which is	"X" document of particular relevances considered novel or cannot be co step when the document is taken	the claimed invention cannot be nsidered to involve an inventive
cited speci	to establish the publication date of another channel of other lail reason (as specified)  ument referring to an oral disclosure, use, exhibition or other	"Y" document of particular relevance	the claimed invention cannot be the step when the document is the such documents, such combination
"P" docu	ment published prior to the international filing date but later than priority date claimed	"&" document member of the same p	atent family
Date of	the actual completion of the international search	Date of mailing of the internation	
4 Oct	ober 1996		
Name a	ind mailing address of the ISA/	Aumorized officer	
Box 50	55, S-102 42 STOCKHOLM	Monika Bohlin Telephone No. +46 8 782 25	00
4 Oct. Name a Swedis Box 50	ober 1996 and mailing address of the ISA/	1 5 -10- 199  Authorized officer  Monika Bohlin	6

### INTERNATIONAL SEARCH REPORT

Information on patent family members

05/09/96

International application No.
PCT/SE 96/00829

Patent document cited in search report		Publication date	Patent family member(s)		Publication date	
EP-A1-	0532766	24/03/93	DE-D,T- KR-B- CA-A- JP-A- US-A- WO-A-	69207128 9512793 2080243 5305699 5527622 9217334	15/05/96 21/10/95 05/10/92 19/11/93 18/06/96 15/10/92	
EP-A2-	0502330	09/09/92	JP-A- US-A-	4255350 5318839	10/09/92 07/06/94	
US-A-	4919984	24/04/90	GB-A,B- JP-A- SE-B,C- SE-A- JP-A-	2163097 61249750 465417 8503098 61011339	19/02/86 06/11/86 09/09/91 22/12/85 18/01/86	

Form PCT/ISA/210 (patent family annex) (July 1992)